

## DIDOTECT F40V-05 M

General information	
<b>Classification</b>	Ready for use mortar
<b>Main raw material components</b>	Fireclay
<b>Bonding type</b>	Air-setting
<b>Grain Size</b>	0-0,5 mm
<b>VDEh-Code</b>	842021201998
<b>Working method</b>	Mortaring
<b>Amount of Material without loss</b>	1,85 t/m <sup>3</sup>
<b>Storage Limit</b>	12 months
<b>Temp. limit for application</b>	1.450 °C

Chemical analysis					
Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	TiO <sub>2</sub>	K <sub>2</sub> O	Na <sub>2</sub> O
40.0%	53.5%	1.1%	1.4%	0.2%	2.8%
Determination on fired substance (1025 °C / 1877 °F) acc. to EN ISO 12677					

The indicated values are standard values, i.e. values taken over a longer representative period of time according to either valid test standards or internal test methods. They may not be regarded as committed specifications and therefore not as guaranteed properties. We reserve the right to further technical developments and new editions of technical product information.

Revision: 19. MAR. 2013